This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problem Mailbox.

3/7/3

DIALOG(R)File 351:Derwent WPI (c) 2004 Thomson Derwent. All rts. reserv.

014334988 **Image available** WPI Acc No: 2002-155691/200221

Covalently and ionically crosslinked polymer preparation, for use as electrochemical and separating membranes, comprises crosslinking acid, sulfinate- and amine-functional polymers

Patent Assignee: UNIV STUTTGART INST CHEM VERFAHRENSTECH (UYST-N); UNIV STUTTGART (UYST-N); KERRES J (KERR-I); TANG C (TANG-I); ZHANG W (ZHAN-I)

Inventor: KERRES J; TANG C; ZHANG W

Number-of Countries: 097 Number of Patents: 009

Patent Family: 7

Patent No Kind Date Applicat No Kind Date Week

DE 10024576 A1 20011122 DE 1024576 A 20000519 200221 B

WO 200187992 A2 20011122 WO 2001EP5644 A 20010517 200221

AU 200181776 A 20011126 AU 200181776 A 20010517 200222

EP 1292632 A2 20030319 EP 2001960223 A 20010517 200322

WO 2001EP5644 A 20010517

BR 200110876 A 20030311 BR 200110876 A 20010517 200323 WO 2001EP5644 A 20010517

KR 2003007583 A 20030123 KR 2002714862 A 20021106 200336

CN 1433442 A 20030730 CN 2001809773 A 20010517 200365

US 20030208014 A1 20031106 WO 2001EP5644 A 20010517 200374 US 2003275854 A 20030512

JP 2003533560 W 20031111 JP 2001585209 A 20010517 200375 WO 2001EP5644 A 20010517

Priority Applications (No Type Date): DE 1024576 A 20000519

Patent Details:

Patent No Kind Lan Pg Main IPC Filing Notes

DE 10024576 A1 11 C08J-005/24

WO₂200187992 A2 G C08F-008/00

Designated States (National): AE AG AL AM AT AU AZ BA BB BG BR BY BZ CA CH CN CO CR CU CZ DE DK DM DZ EC EE ES FI GB GD GE GH GM HR HU ID IL IN IS JP KE KG KP KR KZ LC-LK LR LS LT LU LV MA MD MG MK MN MW MX MZ NO NZ PL PT RO RU SD SE SG SI SK SL TJ TM TR TT TZ UA UG US UZ VN YU ZA ZW Designated States (Regional): AT BE CH CY DE DK EA ES FI FR GB GH GM GR IE IT KE LS LU MC MW MZ NL OA PT SD SE SL SZ TR TZ UG ZW

AU 200181776 A C08F-008/00 Based on patent WO 200187992

EP 1292632 A2 G C08G-075/00 Based on patent WO 200187992

Designated States (Regional): AL AT BE CH CY DE DK ES FI FR GB GR IE IT

LI LT LU LV MC MK NL PT RO SE SI TR

BR 200110876 A C08F-008/00 Based on patent WO 200187992

KR 2003007583 A C08G-075/00

CN 1433442 A C08G-075/00 US 20030208014 A1 C08F-130/04 JP 2003533560 W 50 C08G-085/00 Based on patent WO 200187992

Abstract (Basic): DE 10024576 A1

NOVELTY - Covalently and ionically crosslinked polymers (I) are prepared by crosslinking polymers having acid groups, polymers having sulfinate groups and polymers having tertiary amine groups with polyfunctional haloalkanes or haloaromatics.

DETAILED DESCRIPTION - Covalently and ionically crosslinked polymers (I), including blends of (I) and membranes comprising (I), are prepared by crosslinking polymers having acid groups of formula (II), (III) and/or (IV), polymers having sulfinate groups of formula (V) and polymers having tertiary amine groups of formula (VI) with polyfunctional haloalkanes or haloaromatics to form crosslinks of formula (Ia)-(Ic).

SO3M (II)
PO2M2 (III)
COOM (IV)
SO2M (V)
NR2 (VI)
polymer-SO2-Y-polymer (Ia)
M=H, metal or ammonium;
R=alkyl_hydroxyalkyl or aryl

R=alkyl, hydroxyalkyl or aryl, or NR2 is pyridyl or another tertiary N-containing heteroaromatic or heterocyclic group;

X=Hal or OR;

Hal=F, Cl, Br or I;

Y=(CH2)x, arylene, (CH2)x-arylene or CH2-arylene-CH2; and x=3-12.

An INDEPENDENT CLAIM is also included for the preparation of (I), comprising: dissolving the polymers in N,N-dimethylformamide, N,N-dimethylacetamide, N-methylpyrrolidone (NMP), dimethyl sulfoxide or sulfolane; adding the crosslinker; homogeneously dispersing the crosslinker in the polymer solution by stirring; filtering and degassing the polymer solution; spreading a thin film of the polymer solution on a substrate (e.g. a glass or metal plate or a woven or non-woven fabric); removing the solvent by heating to 80-130 degrees C and/or applying a vacuum or in a circulating-air dryer; optionally removing the film from the substrate; and treating the film in dilute (1-70%) mineral acid and then deionized water at a temperature between room temperature and 95 degrees C.

USE - Membranes comprising (I) are useful both in electrochemical applications, especially fuel cells (operating with hydrogen or methanol at 0-180 degrees C), electrochemical cells, secondary batteries and electrolysis cells, and in membrane separation processes, e.g. gas separation, pervaporation, perstraction, reverse osmosis,

electrodialysis or dialysis.

ADVANTAGE - (I) combine the hydrolytic stability of covalently crosslinked polymers with the flexibility and good water retention of ionically crosslinked polymers.